



Values in mm / nominal

Float Information

@25°C

Material		PP	HF700SA	Black RAL9004		
Weight	g	4.2 +0.5/-0.4				

Magnetical Characteristics

@25°C

Type		NdFeB				
Grade		N35H				
Coating		NiCuNi				
Remanence Br	T	1.17-1.24				
Coercivity HcB	kA/m	≥868				
Coercivity HcJ	kA/m	≥1353				
Energy Product (BH)	kJ/m ³	263-287				

Environmental Characteristics

Operating temperature (max)	°C	80				
-----------------------------	----	----	--	--	--	--